

Model: ASCOT ARCE ANT. 19,3X120(A)

Codes: 100161045

Water absorption: Bla - Porcelánico ($E \leq 0.1\%$)



DIMENSIONAL FEATURES

 UNE-EN ISO 10545-2

Length	1200 MM	
Length and width deviation	Below 0.15%	+/-0.3%*
Side straightness deviation	Below 0.15%	+/-0.3%*
Squareness deviation	Below 0.15%	+/-0.3%*
Surface flatness deviation	Below 0.15%	+/-0.4%*
Thickness	11.5 MM	+/-5%*
Width	193 MM	

*ISO-13006:2018 UNE-EN 14411:2016

MECHANICAL FEATURES

 UNE-EN ISO 10545-4-6-7-11

Abrasion resistance	PEI 4 / 1500v	
Breaking strength	3766.2 N	>1300N*
Crazing resistance	Resists 3 cycles	
Modulus of rupture	57 N/MM2	>=35N/mm2*

*ISO-13006:2018 UNE-EN 14411:2016

HYGIENIC FEATURES

 UNE-EN ISO 10545-13-14:1995

Chemical resistance	Class "A" for swimming pools and cleaning products (resists attack). Minimum Class "B" for acids and bases	B Min.*
Stain resistance	Class 5. Easy cleaning with water	3 Min.*

*ISO-13006:2018 UNE-EN 14411:2016

SCOPE OF USE

Technical code-1	Use on medium traffic floors	
------------------	------------------------------	--

ANTI-SLIP VALUE

 UNE 41901:2017 EX, UNE 41902:2017 EX, DIN-51130 y ASTM C1028

4s	WET-64/DRY-69	
Dynamic coefficient of friction	>0,42	
Slip resistance (bare feet)	C	
Slip resistance (pendulum-wet)	CL3	
Slip resistance (ramp)	R-12	

*ISO-13006:2018 UNE-EN 14411:2016

System Certification



PACKING

Boxes	1.158 M2/BOX	
Pallets	55.5839 M2/PAL	
Units	0.2316 M2/PIECE	

System Certification



Do not use cleaning agents containing hydrofluoric acid.
It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint.
For big sizes, it is recommended to fix with mortars containing polymeric additives and to use the double glueing technique.
Mosaic tiles must be grouted.

This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.