


Model: INDIC 25X44,3(A)

Codes: 100271629 - V57600081

Water absorption: BIII - Revestimiento (10%≤E≤20%)



DIMENSIONAL FEATURES

UNE-EN ISO 10545-2

| | | |
|-----------------------------|-------------|----------|
| Length | 443 MM | |
| Length and width deviation | Below 0.15% | +/-0.3%* |
| Side straightness deviation | Below 0.15% | +/-0.3%* |
| Squareness deviation | Below 0.15% | +/-0.3%* |
| Surface flatness deviation | Below 0.15% | +/-0.4%* |
| Thickness | 8.5 MM | +/-5%* |
| Width | 248.4 MM | |

*ISO-13006:2018 UNE-EN 14411:2016

MECHANICAL FEATURES

UNE-EN ISO 10545-4-6-7-11

| | | |
|---------------------|------------------|------------|
| Abrasion resistance | No Aplica | |
| Breaking strength | 1096 N | >600N* |
| Crazing resistance | Resists 3 cycles | |
| Modulus of rupture | 28 N/MM2 | >=12N/mm2* |

*ISO-13006:2018 UNE-EN 14411:2016

HYGIENIC FEATURES

UNE-EN ISO 10545-13-14:1995

| | | |
|---------------------|--|---------|
| Chemical resistance | Class "A" for swimming pools and cleaning products (resists attack). Minimum Class "B" for acids and bases | B Min.* |
| Stain resistance | Class 5. Easy cleaning with water | 3 Min.* |

*ISO-13006:2018 UNE-EN 14411:2016

SCOPE OF USE

| | | |
|------------------|--------------|--|
| Technical code-1 | Use on walls | |
|------------------|--------------|--|

ANTI-SLIP VALUE

UNE 41901:2017 EX, UNE 41902:2017 EX, DIN-51130 y ASTM C1028

| | | |
|---------------------------------|-----------|--|
| Dynamic coefficient of friction | No Aplica | |
| Slip resistance (bare feet) | No Aplica | |
| Slip resistance (pendulum-wet) | CL0 | |

*ISO-13006:2018 UNE-EN 14411:2016

System Certification



PACKING

| | | |
|---------|-----------------|--|
| Boxes | 1.329 M2/BOX | |
| Pallets | 90.3725 M2/PAL | |
| Units | 0.1108 M2/PIECE | |

System Certification



Do not use cleaning agents containing hydrofluoric acid.
It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint.
For big sizes, it is recommended to fix with mortars containing polymeric additives and to use the double glueing technique.
Mosaic tiles must be grouted.

This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.