

Model: JAPAN MARINE 25X44,3(A)

Codes: 100273021 - P36000121

Water absorption: BIII - Revestimiento (10%≤E≤20%)



DIMENSIONAL FEATURES
UNE-EN ISO 10545-2

Length	443 MM	
Length and width deviation	Below 0.15%	+/-0.3%*
Side straightness deviation	Below 0.15%	+/-0.3%*
Squareness deviation	Below 0.15%	+/-0.3%*
Surface flatness deviation	Below 0.15%	+/-0.4%*
Thickness	8.5 MM	+/-5%*
Width	248.4 MM	

*ISO-13006:2018 UNE-EN 14411:2016

MECHANICAL FEATURES
UNE-EN ISO 10545-4-6-7-11

Abrasion resistance	No Aplica	
Breaking strength	1055 N	>600N*
Crazing resistance	Resists 3 cycles	
Modulus of rupture	24 N/MM2	>=12N/mm2*

*ISO-13006:2018 UNE-EN 14411:2016

HYGIENIC FEATURES
UNE-EN ISO 10545-13-14:1995

Chemical resistance	Class "A" for swimming pools and cleaning products (resists attack). Minimum Class "B" for acids and bases	B Min.*
Stain resistance	Class 5. Easy cleaning with water	3 Min.*

*ISO-13006:2018 UNE-EN 14411:2016

SCOPE OF USE

Technical code-1	Use on walls	
------------------	--------------	--

ANTI-SLIP VALUE
UNE 41901:2017 EX, UNE 41902:2017 EX, DIN-51130 y ASTM C1028

Dynamic coefficient of friction	No Aplica	
Slip resistance (bare feet)	No Aplica	
Slip resistance (pendulum-wet)	CL0	

*ISO-13006:2018 UNE-EN 14411:2016

System Certification



P36000121
100273021

JAPAN MARINE

PORCELANOSA

PORCELANOSA Grupo

PACKING

Boxes	1.329 M2/BOX	
Pallets	90.3725 M2/PAL	
Units	0.1108 M2/PIECE	

System Certification



Do not use cleaning agents containing hydrofluoric acid.
It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint.
For big sizes, it is recommended to fix with mortars containing polymeric additives and to use the double glueing technique.
Mosaic tiles must be grouted.

This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.