

Model: DEVON ROBLE 19,3X180(A)

Codes: 100280176 - P16700751

Water absorption: Bla - Porcelánico (E<=0.1%)



DIMENSIONAL FEATURES
UNE-EN ISO 10545-2

Length	1800 MM	
Length and width deviation	Below 0.15%	+/-0.3%*
Side straightness deviation	Below 0.15%	+/-0.3%*
Squareness deviation	Below 0.15%	+/-0.3%*
Surface flatness deviation	Below 0.15%	+/-0.4%*
Thickness	11.5 MM	+/-5%*
Width	193 MM	

*ISO-13006:2018 UNE-EN 14411:2016

MECHANICAL FEATURES
UNE-EN ISO 10545-4-6-7-11

Abrasion resistance	PEI 3 / 600v	
Breaking strength	4396.3 N	>1300N*
Crazing resistance	Resists 3 cycles	
Modulus of rupture	64.6 N/MM2	>=35N/mm2*

*ISO-13006:2018 UNE-EN 14411:2016

HYGIENIC FEATURES
UNE-EN ISO 10545-13-14:1995

Chemical resistance	Class "A" for swimming pools and cleaning products (resists attack). Minimum Class "B" for acids and bases	B Min.*
Stain resistance	Class 5. Easy cleaning with water	3 Min.*

*ISO-13006:2018 UNE-EN 14411:2016

SCOPE OF USE

Technical code-1	Use on medium traffic floors	
------------------	------------------------------	--

ANTI-SLIP VALUE
UNE 41901:2017 EX, UNE 41902:2017 EX, DIN-51130 y ASTM C1028

Dynamic coefficient of friction	>0,42	
Slip resistance (pendulum-wet)	CL1	
Slip resistance (ramp)	R-10	

*ISO-13006:2018 UNE-EN 14411:2016

System Certification



P16700751
100280176

DEVON ROBLE

PORCELANOSA

PORCELANOSA Grupo

PACKING

Boxes	1.0422 M2/BOX	
Pallets	56.2793 M2/PAL	
Units	0.3474 M2/PIECE	

System Certification



Do not use cleaning agents containing hydrofluoric acid.
It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint.
For big sizes, it is recommended to fix with mortars containing polymeric additives and to use the double glueing technique.
Mosaic tiles must be grouted.

This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.