

Model: MINNESOTA CREAM(24C/P) 25X150(A)

Codes: 100297144

Water absorption: Bla - Porcelánico (E<=0.1%)



MATE / MATT



DETONIFICADO
TONE VARIATIONS



RECTIFICADO
RECTIFIED



DIMENSIONAL FEATURES

UNE-EN ISO 10545-2

Length	1500 MM	
Length and width deviation	Below 0.15%	+/-0.3%*
Side straightness deviation	Below 0.15%	+/-0.3%*
Squareness deviation	Below 0.15%	+/-0.3%*
Surface flatness deviation	Below 0.15%	+/-0.4%*
Thickness	11 MM	+/-5%*
Width	250 MM	

*ISO-13006:2018 UNE-EN 14411:2016

MECHANICAL FEATURES

UNE-EN ISO 10545-4-6-7-11

Abrasion resistance	4 - 1500 Rev.	
Breaking strength	3696 N	>1300N*
Crazing resistance	Resists 3 cycles	
Modulus of rupture	56 N/MM2	>=35N/mm2*

*ISO-13006:2018 UNE-EN 14411:2016

HYGIENIC FEATURES

UNE-EN ISO 10545-13-14:1995

Chemical resistance	Class "A" for swimming pools and cleaning products (resists attack). Minimum Class "B" for acids and bases	B Min.*
Stain resistance	Class 5. Easy cleaning with water	3 Min.*

*ISO-13006:2018 UNE-EN 14411:2016

SCOPE OF USE

Technical code-1	Use on medium traffic floors	
------------------	------------------------------	--

ANTI-SLIP VALUE

UNE 41901:2017 EX, UNE 41902:2017 EX, DIN-51130 y ASTM C1028

Dynamic coefficient of friction	0.58	
Slip resistance (bare feet)	B	
Slip resistance (pendulum-wet)	CL1	
Slip resistance (ramp)	R-10	

*ISO-13006:2018 UNE-EN 14411:2016

System Certification



Do not use cleaning agents containing hydrofluoric acid.

It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint.

For big sizes, it is recommended to fix with mortars containing polymeric additives and to use the double gluing technique.

Mosaic tiles must be grouted.

This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.

PACKING

Boxes	1.875 M2/BOX	
Pallets	44.9994 M2/PAL	
Units	0.375 M2/PIECE	

System Certification



Do not use cleaning agents containing hydrofluoric acid.
It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint.
For big sizes, it is recommended to fix with mortars containing polymeric additives and to use the double glueing technique.
Mosaic tiles must be grouted.

This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.